

TECHNICAL DATA SHEET

JESMONITE® AC100



- **Product Description**

Jesmonite® AC100 is a water-based, two-component, acrylic polymer/mineral resin system. The system is suitable for a wide range of casting and laminating applications where the end user wants to reduce the many risks associated with conventional solvent based systems. A range of ancillary products including decorative and functional fillers, control chemicals, pigments, and glass reinforcements are also provided making the material extremely versatile. The material is suitable for internal and external use, however if used externally a sealer or suitable paint system is recommended to protect surface appearance.

- **Specifications**

Mix Ratio	2.5:1 parts Powder to Liquids ratio by weight
Wet Density	1845 kg/m ³
Dry Density	1745 kg/m ³
Initial set	15 – 20 minutes (18°C, No Retarder)
Expansion on set	0.15%

- **Other Properties**

Compressive Strength	25 – 30 MPa
Tensile Strength (UTS)	25 – 35 Mpa
Bending Elastic Limit (LOP)	15 – 20 Mpa
Bending Strength (MOR)	50 – 65 Mpa
Youngs Modulus	5 – 6 Mpa
Impact Strength (Charpy)	30 KJ/m ²
Moisture Movement	<1%
Fire resistance	B.S.476 Part 6&7 – Class 'O'
Freeze/Thaw resistance	Excellent -Test specimens undamaged
Wet/Dry 50 Cycles	Test specimens undamaged

- **Application Areas**

Cast and laminated decorative mouldings, and with the inclusion of suitable glass reinforcements can be utilised for lightweight, high-impact panels. Jesmonite provides a fire resistant coating for many expanded foams for theme park and theatre props.

- **Key Attributes**

Solvent free – No VOC's
 Good abrasion resistance and impact strength
 High Compressive and tensile strength
 Rapid curing and high early strength gain

- **Packaging**

Liquids are supplied in 1kg, 5kg, and 25kg Canisters, Powders in 5kg and 25kg buckets. Bulk IBC/FIBC supply available on request.

- **Storage**

As a basic rule liquid containers should be kept well sealed to prevent water evaporation and skin forming. They should be stored at a constant temperature between 5-25°C and used within six months. Freezing must be avoided. Powders should be kept dry and stored at 5-25°C.

The above information and recommendations are based upon our experience and are offered merely for advice. They are offered in good faith but without guarantee, as conditions and methods of use are beyond our control. We recommend that the user determine the suitability of the materials for the particular purpose intended.

- **Distributor Details**

Jesmonite Ltd.
 Love Lane Industrial Estate
 Bishops Castle
 Shropshire
 United Kingdom
 Tel:+44 (0) 1588 630302
 Fax:+44 (0) 1588 630304
www.jesmonite.co.uk