

**BREAK-
THROUGH!**

VANEX, INC.
1700 South Shawnee St.
Mt. Vernon, IL 62864
Phone (618) 244-1414
Toll Free (800) 851-7390
Fax (618) 244-1461

TECHNICAL DATA SHEET

PRODUCT: MetaLast Waterborne Metal Primer

PRODUCT CODE: 91-62

DESCRIPTION: A high performance waterborne, rust inhibitive primer for metal surfaces. Use as a first coat on properly prepared metal surfaces. Does not require a topcoat. Excellent resistance to humidity. Recommended for ferrous and non-ferrous metals.

COLOR: Red Oxide

GLOSS: 4-10 on 60 Gloss Meter

APPLICATION: Brush, Pad, Roller, Spray

REDUCTION: Clean water, deionized or distilled preferred; add in small increments. Not more than 12 oz. per gallon.

DRY TIME: To touch - 30-45 minutes
(70 F, 50% R.H.) To handle - 1 hour
Recoat - 2 hours

COVERAGE: Up to 400 sq. ft. per gallon

FILM THICKNESS: 3-4 mils wet

WEIGHT PER GALLON: 9.83 lb.

WEIGHT SOLIDS: 43.31%

VOLUME SOLIDS: 32.26%

VISCOSITY: 20-25 sec. #5 Zahn Cup

VOLATILE ORGANIC CONTENT: 1.70 lb/Gal.
(V.O.C.) 204 gm/liter

ps
7/30/01

Refer to Material Safety Data Sheet for additional information.

Exclusive Remedy

The sole remedy for goods not in conformance with any warranty is replacement of the product or return of the purchase price. Vanex shall not be liable for any other damages, including, but not limited to labor expenses.